



# MATERIALS DATA SHEET

787 Renaissance Parkway | Painesville, OH 44077



## Material Series: AS8130 (f1)

### SERIES DESCRIPTION & APPLICATION

AS8130 is a SMC Product developed for electrical product applications. This product is UL-94 V-0 @ 3.0mm as well as rated f1 for outdoor use. This series provides excellent electrical properties while also providing best in class strength.

General Material Properties		
Property (Test Method)	Value	Units
Specific Gravity (ASTM D792)	1.70-1.80	
Mold Shrinkage (ASTM D955)	0.0015-0.003	in/in
Glass Content	30	%

Mechanical Material Properties (Cut)			
Property (Test Method)	Value (US)	Value (Metric)	Units
Tensile Strength (ASTM D638)	9,000-12,000	60-80	psi (MPa)
Tensile Modulus (ASTM D638)	1.6-1.75 x 10 <sup>6</sup>	11.0-12.0	psi (GPa)
Flexural Strength (ASTM D790)	22,000-30,000	150-205	psi (MPa)
Flexural Modulus (ASTM D790)	1.6-1.9 x 10 <sup>6</sup>	11.0-13.1	psi (GPa)
Notched Izod Impact (ASTM D256)	13-17	700-905	ft-lb/in (J/m)

Mechanical Material Properties (Molded)			
Property (Test Method)	Value (US)	Value (Metric)	Units
Tensile Strength (ASTM D638)	18,000-22,000	125-150	psi (MPa)
Tensile Modulus (ASTM D638)	1.85-2.1 x 10 <sup>6</sup>	12.7-14.4	psi (GPa)
Flexural Strength (ASTM D790)	33,000-36,000	230-250	psi (MPa)
Flexural Modulus (ASTM D790)	2.0-2.2 x 10 <sup>6</sup>	13.8-15.1	psi (GPa)
Notched Izod Impact (ASTM D256)	14-16	750-850	ft-lb/in (J/m)

All property values are based on test performed on standard ASTM test samples and according to standard ASTM test methods unless otherwise indicated. This information is offered solely for your consideration and is to be used as a guide only. No other warranty is implied.

### Contact Us:

#### CORPORATE HEADQUARTERS

10095 Queens Way Chagrin Falls, Ohio 44023-5495

(440) 543-7526 Fax: (440) 543-4691

[www.Altraset.com](http://www.Altraset.com)

Revised: 4/17/25



# MATERIALS DATA SHEET

787 Renaissance Parkway | Painesville, OH 44077



## Thermal and Electrical Material Properties

Property (Test Method)	Value (US)	Value (Metric)	Units
Flammability (UL 94 V0)	Pass 0.12	Pass 3.0	in (mm)
Heat Deflection Temperature (ASTM D648)	TBD	TBD	°F (°C)
UL RTI Elec, Imp, Str (UL 746B)	266, 266, 266	130, 130, 130	°F (°C)
Dielectric Strength (ASTM D149)	360-380	14.1-15.0	Volts/mil (kV/mm)
Arc Track Resistance (ASTM D495)	185+	185+	Seconds

All property values are based on test performed on standard ASTM test samples and according to standard ASTM test methods unless otherwise indicated. This information is offered solely for your consideration and is to be used as a guide only. No other warranty is implied.

### Contact Us:

#### CORPORATE HEADQUARTERS

10095 Queens Way Chagrin Falls, Ohio 44023-5495

(440) 543-7526 Fax: (440) 543-4691

[www.Altraset.com](http://www.Altraset.com)

Revised: 4/17/25